

# TECHNICAL DATA SHEET

Rhino Carbon Fiber™ 400 GSM Unidirectional | Revision Date 6/30/2022

8383 Riley Street,  
Zeeland, MI  
USA 49464  
E: info@rhinocarbonfiber.com

01

## 01: PRODUCT IDENTIFICATION

8383 Riley Street,  
Zeeland, MI  
USA 49464

Product Name: Rhino Carbon Fiber™ 400 GSM Unidirectional

## 02: DESCRIPTION

Rhino Carbon Fiber™ 400 GSM Unidirectional is a high-strength, unidirectional carbon fiber fabric equipped with weft fibers that keep the fabric stable. The material is field laminated using RCF™ Saturant-Adhesive Epoxy to form a carbon fiber reinforced polymer (CFRP) system used to strengthen structural concrete elements.

## 03: WHERE TO USE

- Increase load capacity of structural elements (Beams, Slabs, Columns, Walls, Etc.)
- Restore structural integrity of damaged or deteriorated structural elements
- Repair for damaged or missing reinforcing steel/post tensioning
- Improved blast resistance of concrete, masonry, or stone in mining operations
- Additional Reinforcement to repair/withstand seismic events

## 04: ADVANTAGES

- Used for shear, confinement or flexural strengthening
- Flexible, can be wrapped around complex geometries
- High-Strength
- Lightweight
- Non-corrosive
- Alkali Resistant
- Low aesthetic impact
- Economical

## 05: TYPICAL DATA

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Storage Conditions	Store dry at 40° - 95°F (4° - 35°C)
Shelf Life	Unlimited, if stored properly in original, unopened, undamaged packaging
Color	Black
Primary Fiber Direction	0° (Unidirectional) - Carbon
Areal Density / Weight	400g/m <sup>2</sup> (11.80 oz/yd <sup>2</sup> )

### DRY FIBER PROPERTIES

	Imperial	Metric
Thickness	-0.00866 in	-0.22 mm
Tensile Strength	≥493 ksi	≥ 3400 MPa
Tensile Modulus	≥33358 ksi	≥230 GPa
Elongation at Break %	1.6%	1.6%

### TECHNICAL INFORMATION & COMPOSITE PROPERTIES

	Tested/Experimental Average Value		Design Value		Testing Method
	Imperial	Metric	Imperial	Metric	
Thickness	0.027 in.	0.68 mm	0.027 in.	0.68 mm	ASTM D3039
Tensile Strength	150 ksi	1033.5 MPa	129 ksi	887.8 MPa	ASTM D3039
Tensile Modulus	10620 ksi	73.2 GPa	8790 ksi	60.6 GPa	ASTM D3039
Elongation at Break %	1.40%	1.40%	1.17%	1.17%	ASTM D3039
Tensile Strength per Unit Width	4047 lbs/in.	0.709 kN/mm	3477 lbs/in.	0.609 kN/mm	ASTM D3039

<sup>A</sup>Load and Chord Stiffness per Unit are computed based on CFRP laminate specimen width

<sup>\*</sup>20 sample coupons per test series

<sup>1</sup>Average value of test series

<sup>2</sup>Average value minus 3 standard deviations per ACI440



1-888-684-3889 | www.RhinoCarbonFiber.com

© All Rights Reserved

None of the authors, contributors, administrators, or anyone else connected with Rhino Products USA Inc. or any of its affiliates (collectively, "Rhino"), in any way whatsoever, can be responsible for your use of the information, instructions or advice contained in or linked from this or any related document. All liability with respect to actions taken or not taken based on the contents of this or any related document is hereby expressly disclaimed by Rhino. The content of this document is provided "as is"; no representations are made that the content is error-free.

# TECHNICAL DATA SHEET

Rhino Carbon Fiber™ 400 GSM Unidirectional | Revision Date 6/30/2022

8383 Riley Street,  
Zeeland, MI  
USA 49464  
E: info@rhinocarbonfiber.com

02

## 06: HOW TO USE – SURFACE PREP

---

Surface must be clean, sound, and dry. Remove a light layer of concrete from the surface to allow the epoxy to penetrate the substrate. Typical methods include shot blasting or grinding to achieve this open textured surface. Consult the epoxy adhesive data sheets for additional information on surface preparation.

Existing uneven surfaces must be filled with an appropriate repair mortar/hydraulic cement. The adhesive strength of the concrete must be verified after surface preparation by random pull-off testing (ASTM D-4541) at the discretion of the engineer. Minimum tensile strength, 200 psi (1.4 MPa) with concrete substrate failure.

Round all corners to 1/2" radius in certain "contact critical" applications and at the engineers discretion, a thorough cleaning of the substrate using low pressure sand or water blasting may be sufficient.

## 07: APPLICATION

---

Apply a prime coat of epoxy to the substrate, work the carbon fiber into the epoxy, then add final layer of epoxy to ensure the material is properly saturated. The fabric may also be pre saturated using accepted industry techniques. In either case, installation of this system should be performed only by a trained contractor. In fiber direction, overlapping of the fabric must be at least 6 in or as per the project specifications. Overlapping sections of additional layers should be distributed in location free of other laps.

## 08: TOOLING & FINISHING

---

Fabric can be cut to appropriate lengths by using sharp heavy duty shears. Dull or worn cutting implements can damage, weaken or fray the fabric and their use should be avoided.

## 09: LIMITATIONS

---

- Design calculations must be made and certified by an independent licensed professional engineer.
- System is a vapor barrier. Concrete should not be fully encapsulated in areas of freeze/thaw.



1-888-684-3889 | [www.RhinoCarbonFiber.com](http://www.RhinoCarbonFiber.com)

© All Rights Reserved

None of the authors, contributors, administrators, or anyone else connected with Rhino Products USA Inc. or any of its affiliates (collectively, "Rhino"), in any way whatsoever, can be responsible for your use of the information, instructions or advice contained in or linked from this or any related document. All liability with respect to actions taken or not taken based on the contents of this or any related document is hereby expressly disclaimed by Rhino. The content of this document is provided "as is;" no representations are made that the content is error-free.